



Rubber Expansion Joint Filler for Concrete

Comparing and Contrasting REFLEX Rubber Expansion Joint and Typical Fiber Expansion Joint Properties

	REFLEX	Typical Fiber
Water Absorption:	5%	8 - 14%
Extrusion:	0.143 in	0.05 - 0.15 in
Compression: (to 50% of original)	721 PSI	350 - 485 PSI
Recovery:	90 - 94%	78 - 85%
Standards:	ASTM D 1751 - 97 ASTM D 1752 - 84 AASHTO M-213 - 95 AASHTO M 153 - 98	ASTM D 1751 - 97

REFLEX has also been approved for use by the Department of Transportation in 45 U.S. states and Canadian provinces.

For complete REFLEX test results, contact your JDR Regional Sales at the numbers listed below.



The J D Russell Company

NORTHERN REGION
(800) 888-9708
(586) 296-2700
FAX (586) 296-2757

SOUTHERN REGION
(800) 888-6872
(270) 826-7008
FAX (270) 826-7018

WESTERN REGION
(800) 888-7425
(520) 742-6194
FAX (520) 293-2202

Visit our website at www.jdrussellco.com
Or e-mail us at jdr4@mindspring.com