



Rubber Expansion Joint Filler for Concrete

## Comparing and Contrasting REFLEX Rubber Expansion Joint and Typical Fiber Expansion Joint Properties

	<b>REFLEX</b>	<b>Typical Fiber</b>
<b>Water Absorption:</b>	5%	8 - 14%
<b>Extrusion:</b>	0.143 in	0.05 - 0.15 in
<b>Compression:</b> (to 50% of original)	721 PSI	350 - 485 PSI
<b>Recovery:</b>	90 - 94%	78 - 85%
<b>Standards:</b>	ASTM D 1751 - 97 ASTM D 1752 - 84 AASHTO M-213 - 95 AASHTO M 153 - 98	ASTM D 1751 - 97

REFLEX has also been approved for use by the Department of Transportation in 45 U.S. states and Canadian provinces.

For complete REFLEX test results, contact your JDR Regional Sales at the numbers listed below.



The J D Russell Company

**NORTHERN REGION**  
(800) 888-9708  
(586) 296-2700  
FAX (586) 296-2757

**SOUTHERN REGION**  
(800) 888-6872  
(270) 826-7008  
FAX (270) 826-7018

**WESTERN REGION**  
(800) 888-7425  
(520) 742-6194  
FAX (520) 293-2202

Visit our website at [www.jdrussellco.com](http://www.jdrussellco.com)  
Or e-mail us at [jdr4@mindspring.com](mailto:jdr4@mindspring.com)